

KreteAir 800

(Formerly Krete Air Entraining)

KreteAir 800 is an aqueous solution of Vinsol Resin designed to offer air entrainment in precast concrete products.

FEATURES

- Vinsol Resin Solution

BENEFITS

- No Mixing Required Prior to Use
- Allows Adjustable Entrained Air Content

TECHNICAL INFORMATION

<u>Parameter</u>	<u>Typical Value</u>
Appearance	Dark Brown Liquid
Specific Gravity	1.035
Lbs./Gal	8.63
pH	12.52
IR	Pass

DIRECTIONS FOR USE

1. Use at dosage rate of 2 - 6 fluid ounces per 100 lbs. of cementitious material.
2. Add with the final batch water.
3. For Ribbon Mixers: Mix a maximum of 30 seconds. DO NOT OVER-MIX.
For Pan Mixers: Mix a maximum of 20 seconds. DO NOT OVER-MIX.
4. Check the air content of the resulting precast product.
5. If more entrained air is desired, add additional KreteAir 800 to subsequent batches until the desired air content is achieved.

Note: Dosage and mixing time depends on mix design and thickness of mold.

PRODUCT PACKAGING

Available in 330 US gallon totes, 55 US gallon drums, and 5 US gallon pails. Samples are available by request.

PRODUCT STORAGE AND SHELF LIFE

Store in dry area. Keep containers tightly closed. Do not store in excessively high temperatures (>100 F°). KEEP FROM FREEZING. Avoid physical damage to containers. KreteAir 800 has a rheological shelf life of eight (8) months in original, unopened packaging.

The information presented above is true and accurate to the best of our knowledge. No warranty or guarantee, expressed or implied is made regarding the performance of the product. This information is not intended to be all-inclusive concerning handling, storage and use of the product. Health and other regulatory factors are the responsibility of the customer.

For Industrial Use Only.
Not for internal consumption.
Consult SDS for safety and regulatory information.

PDS - Air 800 - 01/2016